

## Stainless steel electrode

### Classification

AWS A5.4 : E316L-16  
EN 1600 : E 19 12 3 L R 12

### Temperature range

pressurized parts : -120...+350°C  
oxidation resistance : n.a.

### General description

Rutile-basic all position stainless steel electrode for 316L or equivalent steels

Molybdenum level min. 2.7 %

High resistance to general and intergranular corrosion

Smooth weld appearance

Easy slag release

Strong electrode coating

Weldable on AC and DC

Also available in vacuum sealed Sahara ReadyPack® (SRP)

### Welding positions



ISO/ASME PA/1G PB/2F PC/2G PF/3Gup PE/4G PF/5Gup

### Current type

AC / DC + / -

### Approvals

ABS	BV	DNV	GL	LR	RINA	RMRS	TÜV
+	316L	316L	4571	316L	316L	316L	+

### Chemical composition (w%), typical, all weld metal

C	Mn	Si	Cr	Ni	Mo	FN
0.02	0.8	0.8	18.0	11.5	2.85	04-10

### Mechanical properties, all weld metal

	Condition	0.2% Proof strength (N/mm <sup>2</sup> )	Tensile strength (N/mm <sup>2</sup> )	Elongation (%)	Impact ISO-V(J)	
					-20°C	-120°C
Required: AWS A5.4 EN 1600		not required min. 320	min. 490 min. 510	min. 30 min. 25	not required not required	
Typical values	AW	450	580	39	60	40

### Packaging and available sizes

	Diameter (mm)	1.5	2.0	2.5	3.2	4.0	5.0
	Length (mm)	250	300	350	350	350	350
Unit: Box	Pieces / unit	160	225	135	150	90	65
	Net weight/unit (kg)	0.8	2.4	2.7	4.9	4.8	5.0
Unit: SRP	Pieces / unit		84	69	56	29	
	Net weight/unit (kg)		0.9	1.4	1.8	1.5	
Unit: Linc Can™	Pieces / unit			217	134	80	
	Net weight/unit (kg)			4.7	4.4	4.2	

### Identification

Imprint: 316L-16 / AROSTA 316 L

Tip Color: pink

Arosta® 316L: rev. EN 22

## Materials to be welded

Steel grades	EN 10088-1/-2	EN 102 13-4	W.Nr.	ASTM/ACI A240/A312/A351	UNS
<b>Extra low carbon (C &lt;0.03%)</b>					
	X2 CrNiMo 17-12-2		1.4404	(TP)316L CF-3M	S31603 J92800
	X2 CrNiMo 18-14-3		1.4435	(TP)316L	S31603
	X2 CrNiMoN 17-11-2		1.4406	(TP)316LN	S31653
	X2 CrNiMoN 17-13-3		1.4429		
<b>Medium carbon (C &gt;0.03%)</b>					
	X4 CrNiMo 17-12-2		1.4401	(TP)316	S31600
	X4 CrNiMo 17-13-3		1.4436		
		GX5 CrNiMo 19-11	1.4408	CF 8M	J92900
<b>Ti-, Nb stabilized</b>					
	X6 CrNiMoTi 17-12-2		1.4571	316Ti	S31635
	X6 CrNiMoNb 17-12-2		1.4580	316Cb	S31640
	X6 CrNiNb 18-10		1.4550	(TP)347	S34700
		GX5 CrNiNb 19-10	1.4552	CF-8C	J92710

## Calculation data

Sizes Diam. x length (mm)	Current range (A)	Current type	Arc time - per electrode at max. current - (s)*	Energy E(kJ)	Dep.rate H(kg/h)	Weight/ 1000 pcs. (kg)	Electrodes/ kg weldmetal B	kg Electrodes/ kg weldmetal 1/N
1.5 x 250	20 - 40	DC+	25	19	0.44	5.8	330	1.92
2.0 x 300	30 - 50	DC+	42	44	0.58	10.7	150	1.61
2.5 x 350	40 - 75	DC+	50	86	0.88	19.9	82	1.61
3.2 x 350	60 - 110	DC+	57	157	1.3	32.9	49	1.61
4.0 x 350	80 - 150	DC+	64	240	1.7	49.2	32	1.59
5.0 x 350	140 - 220	DC+	67	396	2.6	77.1	20	1.59

\* stub end 35 mm

## Welding parameters, optimum fill passes

Welding positions Diameter (mm)	PA/1G	PB/2F	PC/2G	PF/3G up	PE/4G	PF/5G up
1.5		35A	35A			
2.0		45A	45A	40A	40A	40A
2.5	70A	70A	70A	60A	60A	60A
3.2	100A	100A	100A	70A	70A	70A
4.0	140A	140A	140A	80A		
5.0	180A	180A	180A			

For root passes DC- is recommended.