

Stainless steel electrode

Classification

AWS A5.4 : E318-15*
EN 1600 : E 19 12 3 Nb B 22

Temperature range

*: Deviation, see remarks

General description


Basic coated electrode for stabilized CrNiMo-steels

Service temperature up to 400°C

Good bridging properties

Specially developed for highly restrained structures

Welding positions



Current type

DC + / -

Chemical composition (w%), typical, all weld metal

C	Mn	Si	Cr	Ni	Mo	Nb	FN
0.025	1.5	0.4	18.0	11.0	2.7	0.5	06-12

Mechanical properties, all weld metal

	Condition	0.2% Proof strength (N/mm ²)	Tensile strength (N/mm ²)	Elongation (%)	Impact ISO-V(J) +20°C
Required: AWS A5.4		not required	min. 550	min. 25	not required
EN 1600		min. 350	min. 550	min. 25	not required
Typical values	AW	430	650	30	90

Packaging and available sizes

	Diameter (mm)	2.5	3.2	4.0
	Length (mm)	350	350	350
Unit: Box	Pieces / unit	135	150	100
	Net weight/unit (kg)	2.6	4.8	4.6

Identification

Imprint: JUNGO 318

Tip Color: red

Jungo® 318: rev. EN 21

Materials to be welded

Steel grades	EN 10088-1/-2	EN 102 13-4	W.Nr.	ASTM/ACI A240/A312/A351	UNS
Extra low carbon (C <0.03%)					
	X2 CrNiMo 17-12-2		1.4404	(TP)316L CF-3M	S31603 J92800
	X2 CrNiMo 18-14-3		1.4435	(TP)316L	S31603
	X2 CrNiMoN 17-11-2		1.4406	(TP)316LN	S31653
	X2 CrNiMoN 17-13-3		1.4429		
Medium carbon (C >0.03%)					
	X4 CrNiMo 17-12-2		1.4401	(TP)316	S31600
	X4 CrNiMo 17-13-3		1.4436		
		GX5 CrNiMo 19-11	1.4408	CF 8M	J92900
Ti-, Nb stabilized					
	X6 CrNiMoTi 17-12-2		1.4571	316Ti	S31635
	X6 CrNiMoNb 17-12-2		1.4580	316Cb	S31640
	X6 CrNiNb 18-10		1.4550	(TP)347	S34700
		GX5 CrNiNb 19-10	1.4552	CF-8C	J92710

Calculation data

Sizes Diam. x length (mm)	Current range (A)	Current type	Arc time - per electrode at max. current - (s)*	Energy E(kJ)	Dep.rate H(kg/h)	Weight/ 1000 pcs. (kg)	Electrodes/ kg weldmetal B	kg Electrodes/ kg weldmetal 1/N
2.5 x 350	50 - 70	DC+	50	86	0.82	17.6	88	1.89
3.2 x 350	80 - 100	DC+	51	135	1.3	28.5	53	1.72
4.0 x 350	100 - 130	DC+	66	206	1.7	43.8	32	1.56

* stub end 35 mm

Welding parameters, optimum fill passes

Welding positions Diameter (mm)	PA/1G	PB/2F	PC/2G	PF/3G up	PE/4G	PF/5G up
2.5	60A	60A	60A	60A	60A	60A
3.2	95A	90A	90A	75A	75A	75A
4.0	125A	110A	125A	100A	100A	100A

Remarks/ Application advice

Deviations: chemical composition:

Ni = 10.0 - 13.0%

AWS: Ni = 11.0 - 14.0%